



Product Name CIA	Thinner Clean water. Thin up to 10%-15% for the first coat. Thin up to 20%-30% for the following coats.
Technical Name Flat smooth finish Acrylic Emulsion	Preparation All surfaces to be painted should be clean, dry and free from loose & flaking material. Rub down & rinse. Prime with Colors stabilizers where necessary.
Key Properties <ul style="list-style-type: none"> • Washable • Good hiding power and opacity, very good durability. • Reduced dirt pick up • Very low water absorption • CIA offers enhanced resistance to flame spread. • Very low VOC content • Odorless • Over 100,000 colors available through the automated tinting system. 	Instructions Stir well. Easy to apply by brush, roller or airless spray. Do not apply at temperatures below 5C or when rain is expected.
Recommended Uses Interior & exterior applications	Cleaning Remove as much product as possible from application equipment before cleaning. Clean equipment immediately after use with warm soapy water & rinse thoroughly. Do not empty product into drains or watercourses.
Type of Substrate Plaster, embossed wall coverings, gypsum board, concrete, cement rendering, brickwork & block work.	Additional Info <ul style="list-style-type: none"> • Contains no added lead. • Product batches are tested using a quality control system. • DOW technology • Adhesion 0.5N/mm² based on ASTM D4541 • Scrubability higher than 1000 cycles based on ASTM D4213 conforms to Libnor 1999:84&83 for external emulsion paint.
Finish Flat 1/10	Pack Size <ul style="list-style-type: none"> • 1US Quart – (0.945 liters) • 1US Gallon – (3.785 liters) • 1US Drum – (18.925 liters)
Coverage Approximately 10-11 square meters per liter	Transportation & Storage Care should be taken to avoid spillage. Protect from frost & humidity.
Drying Time Touch-dry in 1/2-1 hour Re-coatable after 2-4 hours	

The information submitted in this manual is correct to the best of our knowledge & experience. No liability whatsoever can be accepted on the basis of the information supplied herein.
 Tel: 00961 1 303414-305649-306966-819672 Beirut-Lebanon. Fax: 961-1-816428. E-mail: kassaa@kassaa.com.