



**Product Name**

STUCCO

**Technical Name**

Marble simulation paste  
High gloss smooth finish

**Key Properties**

- Unleaded
- Washable
- Could be protected by applying "Cera wax"
- Non-flammable
- Odorless
- Mirror finish obtained in 3 to 5 coats.
- Reduced dirt pick up
- Very low VOC content
- Over 100,000 colors available through the automated tinting system.

**Recommended Uses**

Internal & external applications

**Type of Substrate**

Plaster, embossed wall coverings, gypsum board, concrete, cement rendering, brickwork & block work

**Finish**

Semi to high gloss finish depending on the application procedure

**Coverage**

Approximately 2.5 square meters per kg.

**Drying Time**

Touch-dry in 1 hour  
Re-coatable after 2-4 hours

**Thinner**

Clean water  
No thinning is required.

**Preparation**

All surfaces to be painted should be clean, dry and free from loose & flaking material. Rub down & rinse.

Prime the substrate with UNDERCOAT, SEALER or PRIMER (stabilizers range).

**Instructions**

Using a stainless steel trowel cover with successive coats of STUCCO until the desired finish is achieved. After 20 minutes of final coat, rub down with a 2000grade sand paper or press down with the trowel to get the final shiny effect.

Do not apply at temperatures below 5C or when rain is expected.

**Cleaning**

Remove as much product as possible from application equipment before cleaning. Clean equipment immediately after use with warm soapy water & rinse thoroughly.

Do not empty product into drains or watercourses.

**Additional Info**

- Product batches are tested using a quality control system.
- Adhesion 0.5N/mm<sup>2</sup> based on ASTM D4541
- Scrubability higher than 1000 cycles based on ASTM D4213

**Pack Size**

- 1US Quart – (0.945 liters)
- 1US Gallon – (3.785 liters)
- 1US Drum – (18.925 liters)

**Transportation & Storage**

Care should be taken to avoid spillage.  
Protect from frost & humidity.

The information submitted in this manual is correct to the best of our knowledge & experience. No liability whatsoever can be accepted on the basis of the information supplied herein.

Tel: 00961 1 303414-305649-306966-819672 Beirut-Lebanon. Fax: 961-1-816428. E-mail: [kassaa@kassaa.com](mailto:kassaa@kassaa.com) .