

ARES

Technical data

NAME:	ARES												
GROUP:	water-based primer												
UTILISATION:	specific primer for POLISTOF (water-based paint) application cycle												
COMPOSITION:	acrylic resins and special transpiration-inducing particles.												
DISSOLVENT:	water												
CHARACTERISTICS:	<table> <tr> <td>specific weight:</td> <td>1450 ± 30 gr/LT. at 25°C</td> </tr> <tr> <td>viscosity:</td> <td>5600±500cps (Brookfield viscosity meter)</td> </tr> <tr> <td>yield:</td> <td>10 m²/LT.</td> </tr> <tr> <td>appearance:</td> <td>matt</td> </tr> <tr> <td>colour:</td> <td>white</td> </tr> <tr> <td>packing:</td> <td>cans of 0,5 LT. - 2,5 LT.</td> </tr> </table>	specific weight:	1450 ± 30 gr/LT. at 25°C	viscosity:	5600±500cps (Brookfield viscosity meter)	yield:	10 m ² /LT.	appearance:	matt	colour:	white	packing:	cans of 0,5 LT. - 2,5 LT.
specific weight:	1450 ± 30 gr/LT. at 25°C												
viscosity:	5600±500cps (Brookfield viscosity meter)												
yield:	10 m ² /LT.												
appearance:	matt												
colour:	white												
packing:	cans of 0,5 LT. - 2,5 LT.												
DRYING TIME:	<table> <tr> <td>on surface:</td> <td>2hrs at 20°C</td> </tr> <tr> <td>2nd coat:</td> <td>4hrs at 20°C</td> </tr> <tr> <td>in depth:</td> <td>24hrs at 20°C</td> </tr> </table>	on surface:	2hrs at 20°C	2nd coat:	4hrs at 20°C	in depth:	24hrs at 20°C						
on surface:	2hrs at 20°C												
2nd coat:	4hrs at 20°C												
in depth:	24hrs at 20°C												

CHARACTERISTICS AND DURABILITY:

The product is extremely durable in rural, marine and industrial environments and it perfectly adheres onto the most difficult surfaces. The micro-porous structure of the primer allows transpiration of vapour on any type of walls. ARES primer has been specially created as a firmly-adhering indispensable primer coating for POLISTOF water-based paint cycle. Improve POLISTOF covering , colouring ARES primer with water based ADDITIVAL pigment in order to obtain a tone of colour similar to POLISTOF finishing paint.

PREPARATION

OF PRODUCT:	dilution:	ready to use if applied by a brush. To be diluted with 10% of water if applied with a gun
APPLICATION:	tools:	brush or gun
	number of coats:	one or more

PREPARATION

OF THE SURFACE: Evaluate the surface condition and take away any old paint not properly stuck on the wall. If necessary, plaster the wall and then sand it. In case of damaged/crumbling surfaces, apply one coat of ARES primer as a fixative, mixed with water in the proportion of 1:1. After 4 hours at a temperature of 20°C apply another coat of ARES without diluting it.

NOTE:

Application temperature and storage should be between +5°C and +35°C. Protect against cold. Wash the tools in water immediately after application.

**The technical sheet no SC 00110 has been prepared by the Quality Control Department.
Edition no. 4 - January, 2001**