

STUCCO VENEZIANO

<u>NAME:</u>	STUCCO VENEZIANO												
<u>TYPE:</u>	mineral coating for interior												
<u>USE:</u>	decoration of civil plasters for interior; to apply after a normal preparation of the mural works.												
<u>TECHNICAL DATA:</u>	<table> <tr> <td>specific weight:</td> <td>1700 ± 30 gr/lit at 25°C</td> </tr> <tr> <td>viscosity:</td> <td>===</td> </tr> <tr> <td>yield:</td> <td>Kg 0,6 per m² on smooth plaster</td> </tr> <tr> <td>aspect:</td> <td>shiny, with distinctive feature</td> </tr> <tr> <td>colours:</td> <td>see catalogue</td> </tr> <tr> <td>packaging:</td> <td>cans of 1 lt. - 4 lt. - 25 kg.</td> </tr> </table>	specific weight:	1700 ± 30 gr/lit at 25°C	viscosity:	===	yield:	Kg 0,6 per m ² on smooth plaster	aspect:	shiny, with distinctive feature	colours:	see catalogue	packaging:	cans of 1 lt. - 4 lt. - 25 kg.
specific weight:	1700 ± 30 gr/lit at 25°C												
viscosity:	===												
yield:	Kg 0,6 per m ² on smooth plaster												
aspect:	shiny, with distinctive feature												
colours:	see catalogue												
packaging:	cans of 1 lt. - 4 lt. - 25 kg.												
<u>DRYING TIME:</u>	<table> <tr> <td>on the surface:</td> <td>2 hours at 20 °C</td> </tr> <tr> <td>over painting:</td> <td>===</td> </tr> <tr> <td>below the surface:</td> <td>5 hours at 20 °C</td> </tr> <tr> <td>sanding:</td> <td>after 5 hours</td> </tr> </table>	on the surface:	2 hours at 20 °C	over painting:	===	below the surface:	5 hours at 20 °C	sanding:	after 5 hours				
on the surface:	2 hours at 20 °C												
over painting:	===												
below the surface:	5 hours at 20 °C												
sanding:	after 5 hours												
<u>CHARACTERISTICS AND RESISTANCE:</u>	high degree of walls traspiration. Suitable to obtien decoration and refined glossy particular effects												
<u>PREPARATION OF THE SURFACE:</u>	<p>Available colours: white - other colours may be obtained with manual system that is adding the Additival: Serie 0050 for 1 lt. can; Serie 0125 for 4 lt. can; 0750 for Kg. 25 can. Mix with high velocity mechanical agitator. For quantity superior of 300 Kg. may be asked an already colorated can.</p> <p>a - Prepare the surface in the usual way and follow with one or two coats of transparent or colorated Fissativo Gummiflex.</p> <p>b - Cover with successive coats of STUCCO VENEZIANO to obtain a smooth and uniform surface.</p> <p>c - After about 5 hours, remove all imperfections with fine sandpaper.</p> <p>d - The final coats of STUCCO VENEZIANO should be applied with a stainless steel spatula, the size of which will depend on the required final effect.</p> <p>e - After approximately 20 minutes, smooth out the surface using extra-fine sandpaper (737 SP) with circular movements, exercising moderate pressure where transparent effect is required.</p> <p>f - If it is necessary to give a better protection to the surface, is recomanded to apply Cera Lucidante 370 with a woolen cloth, which light the chosen colours.</p>												
<u>PREPARATION OF THE PRODUCT:</u>	<table> <tr> <td>thinning:</td> <td>ready for use</td> </tr> <tr> <td>catalization relation:</td> <td>===</td> </tr> <tr> <td>pot life:</td> <td>===</td> </tr> </table>	thinning:	ready for use	catalization relation:	===	pot life:	===						
thinning:	ready for use												
catalization relation:	===												
pot life:	===												
<u>APPLICATION:</u>	<table> <tr> <td>system:</td> <td>stainless steel spatula</td> </tr> <tr> <td>coats:</td> <td>2 or more</td> </tr> </table>	system:	stainless steel spatula	coats:	2 or more								
system:	stainless steel spatula												
coats:	2 or more												

NOTE:

Wash the tools with water immediately after use. Keep away from frozen places